

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau(43) International Publication Date
27 June 2002 (27.06.2002)

PCT

(10) International Publication Number
WO 02/50201 A1(51) International Patent Classification⁷: **C09D 167/02**(21) International Application Number: **PCT/EP01/14889**(22) International Filing Date:
17 December 2001 (17.12.2001)(25) Filing Language: **English**(26) Publication Language: **English**(30) Priority Data:
00128098.1 21 December 2000 (21.12.2000) **EP**(71) Applicant (*for all designated States except US*): **UCB, S.A.** [BE/BE]; Allée de la Recherche, 60, B-1070 Bruxelles (BE).

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): **MOENS, Luc** [BE/BE]; Ijsvogellaan, 30, B-1640 Sint-Genesius-Rode (BE). **KNOOPS, Nele** [BE/BE]; Blokweg 12, B-3020 Herent (BE). **MAETENS, Daniel** [BE/BE]; Avenue René Comhaire, 108, B-1070 Bruxelles (BE).(74) Agent: **ROELANTS, François**; UCB, S.A., Intellectual Property Department, Allée de la Recherche, 60, B-1070 Bruxelles (BE).(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).**Published:**

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments
- entirely in electronic form (except for this front page) and available upon request from the International Bureau

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: **POWDERED THERMOSETTING COMPOSITION FOR COATINGS**

(57) **Abstract:** The present invention relates to powdered thermosetting compositions including a binder which comprises a carboxyl group containing amorphous isophthalic acid containing polyester, a carboxyl group containing aliphatic semi-crystalline polyester, an optional and different carboxyl group containing semi-crystalline polyester, at least 5 parts by weight, based on the total weight of the binder, of a specific glycidyl group containing acrylic copolymer and a curing agent having functional groups reactive with the polyesters' carboxyl groups. The powdered thermosetting compositions are useful for the preparation of powdered paints and varnishes which give semi-matt coatings having an outstanding flow, a remarkable weatherability and excellent mechanical properties.

WO 02/50201 A1

Powdered thermosetting composition for coatings

The present invention relates to powdered thermosetting compositions comprising as binder a co-reactable particulate mixture of a carboxyl group containing amorphous polyester, a carboxyl group containing aliphatic semi-crystalline polyester, a glycidyl group containing acrylic copolymer and a β -hydroxyalkylamide group containing curing agent whose functional groups are reactive with the polyesters' carboxyl groups. Optionally, the compositions may contain another carboxyl group containing semi-crystalline polyester. The invention also relates to the use of said compositions for the preparation of powdered paints and varnishes which give semi-matt coatings providing an outstanding flow, a remarkable weatherability and excellent mechanical properties. The invention further relates to the semi-matt coatings obtainable from said compositions.

Powdered thermosetting compositions are widely used as paints and varnishes for coating the most various articles. These powders have numerous advantages. On the one hand the problems associated with solvents are completely eliminated and on the other hand the powders are not wasted, since only the powder in direct contact with the article is retained on the article, any excess powder being, in principle, entirely recoverable and reusable. For these and other reasons, powdered coating compositions are preferred to coating compositions in the form of solutions in e.g. organic solvents.

Powdered coating compositions should give coatings which have a good adhesion to metal substrates like steel or aluminium, a nice flow without defects and orange peel, a good flexibility and weatherability as well as a good chemical resistance. Besides, powdered coating compositions should exhibit a sufficiently high glass transition temperature to avoid reagglomeration during handling, transportation and storage.

The majority of today's coating compositions provide coatings having a high gloss after fusion and curing. The gloss measured at an angle of 60° in accordance with ASTM D523 is in fact often equal to or indeed even greater than 90%.

For example, WO 97/20895 discloses powdered thermosetting compositions including a binder consisting of a mixture of semi-crystalline and amorphous polyesters containing carboxyl groups, and a cross-linking agent with functional groups capable of reacting with the carboxyl groups of the polyesters. The powdered thermosetting compositions are useful for preparing powdered varnishes and paints and provide coatings having a remarkable weather resistance, high gloss and excellent mechanical properties.

CONFIRMATION COPY

WO 91/14745 discloses a thermosetting powder coating composition comprising as binder a co-reactable particulate mixture of a carboxylic acid-functional semi-crystalline polyester component and a curing agent having groups reactable with carboxylic acid groups. The composition may, if desired, include an amorphous polyester, which is said to afford coatings with improved weathering performance and improved resistance to gloss reduction of the coating during outdoor exposure. So-called "hybrid" powder coating compositions comprise an epoxy resin as a co-reactable curing agent. Polyglycidyl-functional acrylic polymers are mentioned among numerous other epoxy resins. The coatings obtained from these thermosetting powder compositions exhibit a high gloss.

While powdered compositions which provide high gloss coatings with good appearance and mechanical properties as well as good weather resistance are known, there is an increasing demand for powdered paints and varnishes which provide matt or semi-matt coatings of good quality, for example for coating certain accessories in the automotive industry, such as wheel rims, bumpers and the like, or for coating metal panels and beams used in construction.

Thus, various methods for manufacturing powdered paints and varnishes that provide matt or semi-matt coatings, have been proposed.

According to one of these methods one or more matting agents, such as described in US 4,242,253, are introduced into the powdered composition, in addition to the binder and conventional pigments.

US 3,842,035 relates to a heat curable powder coating composition which, upon curing, gives a matt finish and which comprises a mixture of a slow curing and a fast curing thermosetting powder composition. The two compositions are extruded separately before dry-blending.

WO 92/01756 describes powder coating compositions comprised of one or more semi-crystalline hydroxyl polyesters, one or more amorphous polyesters and one or more hydroxyl acrylic polymers and a blocked polyisocyanate cross-linking agent. Coatings of the compositions on shaped metal articles exhibit an ASTM D-523-85 60° gloss value of not greater than 35.

In EP-A-0 551 064 powdered thermosetting compositions comprising as binder a mixture of a linear carboxyl group containing polyester and a glycidyl group containing acrylic copolymer are described. The acrylic polymer must have a number averaged molecular weight (Mn) of 4000 to 10000 in order to obtain coatings with useful physical properties. The compositions are useful for the preparation of powdered paints and varnishes which produce matt finishes having

a gloss value measured at an angle of 60° in accordance with ASTM D523 equal to or less than 15.

5 Despite the existing variability of methods for producing matt or semi-matt finishes, experience has shown that these methods are all subject to one or more disadvantages attributed to problems of processing, as well as to overall coating performances. Problems are particularly relating to reproducibility and reliability of the gloss value.

10 There is thus still a need for powdered thermosetting compositions, capable of producing semi-matt coatings which do not exhibit the defects and drawbacks of the prior art.

15 In addition there is a sustained effort to improve flexibility and weatherability of the semi-matt finishes in order to get them appropriate for applications such as coil coating, for example intended for outdoor construction purposes, especially for use in regions having a tropical climate.

20 However, when semi-matt finishes are considered, no method is known today for preparing thermosetting powdered compositions from a single extrusion, which, upon curing, provide criteria such as outstanding flow, remarkable weatherability and excellent flexibility and for which low gloss values are perceived in a reproducible and reliable manner.

25 According to the present invention, it now has been surprisingly found that by using as binder a co-reactable particulate mixture of a carboxyl group containing amorphous isophthalic acid containing polyester, a carboxyl group containing aliphatic semi-crystalline polyester, optionally another carboxyl group containing semi-crystalline polyester, at least 5 parts by weight of a specific glycidyl group containing acrylic copolymer and a β -hydroxyalkylamide group containing curing agent having functional groups reactive with the polyesters' carboxyl groups, it is possible to obtain powdered thermosetting compositions which produce coatings exhibiting the desired characteristics.

30

Thus, according to the present invention there is provided a powdered thermosetting composition including a binder which comprises

- 35 (a) a carboxyl group containing amorphous isophthalic acid containing polyester,
(b) a carboxyl group containing aliphatic semi-crystalline polyester,
(c) optionally, a carboxyl group containing semi-crystalline polyester other than (b);
(d) at least 5 parts by weight, based on the total weight of the binder, of a glycidyl group containing acrylic copolymer, said copolymer comprising at least 10 mole% of a

glycidyl group containing monomer and having a number averaged molecular weight (Mn) of 10000 or less, and

- (e) a β -hydroxyalkylamide group containing curing agent whose functional groups are reactive with the polyesters' carboxyl groups.

5

The present composition is useful for preparing semi-matt coatings, i.e. coatings having a gloss value measured at an angle of 60° in accordance with ASTM D523 between, 20 and 80.

In the sense of the present application the term "isophthalic acid containing polyester" refers to a polyester which is composed of at least 10 mole% of isophthalic acid, preferably at least 50 mole% based on the total acid constituents of the polyester.

10

The amorphous polyester and the semi-crystalline polyesters independently may be linear or branched.

15

The carboxyl group containing amorphous polyester (a) of the present composition is preferably composed of, referring to the acid constituents, from 10 to 100 mole% of isophthalic acid, preferably 50 to 100 moles%, and from 90 to 0 mole% of another diacid, such as an aliphatic, cycloaliphatic or aromatic diacid, and, referring to the alcohol constituents, from 35 to 100 mole% of neopentyl glycol and/or 2-butyl-2-ethyl-1,3-propanediol and from 65 to 0 mole% of another diol, such as an aliphatic or cycloaliphatic diol. Branching of the amorphous polyester can be obtained by incorporation of a polyacid or polyol.

20

The acid constituent of the amorphous polyester, which is not the isophthalic acid, may preferably be selected from one or more aliphatic, cycloaliphatic or aromatic diacids, such as fumaric acid, maleic acid, phthalic acid, terephthalic acid, 1,4-cyclohexanedicarboxylic acid, 1,3-cyclohexanedicarboxylic acid, 1,2-cyclohexanedicarboxylic acid, succinic acid, adipic acid, glutaric acid, pimelic acid, suberic acid, azelaic acid, sebacic acid, 1,12-dodecanedioic acid, etc., or the corresponding anhydrides.

25

30

Incorporation of e.g. up to 15 mole% relative to the diacid, of polyacids having at least three carboxylic acid groups such as trimellitic acid or pyromellitic acid or their corresponding anhydrides or mixtures thereof, induces branching of the polyester.

The glycol constituent of the amorphous polyester, which is not the neopentyl glycol and/or 2-butyl-2-ethyl-1,3-propanediol, may preferably be selected from one or more aliphatic or cycloaliphatic glycols, such as ethylene glycol, propylene glycol, 1,4-butanediol, 1,6-

35

hexanediol, 1,4-cyclohexanediol, 1,4-cyclohexanedimethanol, 2-methyl-1,3-propanediol, hydrogenated Bisphenol A, hydroxypivalate of neopentyl glycol, etc.

5 Incorporation of e.g. up to 15 mole% relative to the neopentyl glycol and/or 2-butyl-2-ethyl-1,3-propanediol, of trifunctional or tetrafunctional polyols such as trimethylolpropane, di-trimethylolpropane, pentaerythritol or mixtures thereof, induces branching of the polyester.

10 The carboxyl group containing amorphous polyesters (a) of the present composition preferably have an acid number (AN) from 15 to 70 mg KOH/g and in particular from 20 to 50 mg KOH/g.

The carboxyl group containing amorphous polyesters are advantageously further characterised by:

- 15 - a number averaged molecular weight (M_n) ranging from 1600 to 11000 and preferably from 2200 to 5600, measured by gel permeation chromatography (GPC);
- a glass transition temperature (T_g) from 40 to 80°C, measured by Differential Scanning Calorimetry according to ASTM D3418 with a heating gradient of 20°C per minute; and
- 20 - an ICI (cone/plate) viscosity accordingly to ASTM D4287-88, measured at 200°C ranging from 5 to 15000 mPa.s.

25 The carboxyl group containing amorphous polyester may fulfill one or more of the above conditions for its acid number, its number averaged molecular weight, its glass transition temperature and its ICI viscosity. Preferably, the amorphous polyester, however, fulfills all of these requirements.

30 The carboxyl functional aliphatic semi-crystalline polyester (b) is composed of, referring to the acid constituents, 40 to 100 mole% of a linear chain dicarboxylic acid containing 10 to 16 carbon atoms and 0 to 60 mole% of at least one linear chain dicarboxylic acid containing 4 to 9 carbon atoms. The alcohol constituents of the carboxyl functional aliphatic semi-crystalline polyester (b) is selected from at least one aliphatic non-branched or cycloaliphatic diol containing 2 to 16 carbon atoms.

35 The linear chain dicarboxylic acid containing 10 to 16 carbon atoms of the carboxylic functional aliphatic semi-crystalline polyester (b) is selected among 1,10-decanedioic acid, 1,11-undecanedioic acid, 1,12-dodecanedioic acid, 1,13-tridecanedioic acid, 1,14-tetradecanedioic acid, 1,15-pentadecanedioic acid, 1,16-hexadecanedioic acid, used in a mixture or alone.

The linear chain dicarboxylic acid containing 4 to 9 carbon atoms of the carboxyl functional aliphatic semi-crystalline polyester (b) is selected from succinic acid, adipic acid, glutaric acid, pimelic acid, suberic acid, azealic acid. The aliphatic non-branched or cycloaliphatic diol containing 2 to 16 carbon atoms of the carboxyl functional aliphatic semi-crystalline polyester (b) is selected from ethylene glycol, 1,3-propanediol, 1,4-butanediol, 1,5-pentanediol, 1,6-hexanediol, 1,7-heptanediol, 1,8-octanediol, 1,9-nonanediol, 1,10-decanediol, 1,12-dodecanediol, 1,14-tetradecanediol, 1,16-hexadecanediol or 1,4-cyclohexanediol, 1,4-cyclohexanedimethanol, hydrogenated Bisphenol A, 2,2,4,4-tetramethyl-1,3-cyclobutanediol or 4,8-bis(hydroxy-methyl)tricyclo[5.2.1.0^{2,6}]decane, used as a mixture or alone.

The second carboxyl functional semi-crystalline polyester (c), optionally used in the formulation of the present invention, is composed of from 75 to 100 mole% of terephthalic acid and/or of 1,4-cyclohexanedicarboxylic acid and/or a linear chain dicarboxylic acid containing 4 to 9 carbon atoms and from 25 to 0 mole% of another aliphatic, cycloaliphatic or aromatic diacid.

The alcohol constituent of the second carboxyl functional semi-crystalline polyester (c), optionally used in the formulation of the present invention, is composed of from 75 to 100 mole% of a cycloaliphatic or linear chain diol containing 2 to 16 carbon atom and from 25 to 0 mole% of another aliphatic glycol.

The linear chain dicarboxylic acid containing 4 to 9 carbon atoms of the second optional carboxyl functional semi-crystalline polyester (c) is selected among succinic acid, adipic acid, glutaric acid, pimelic acid, suberic acid and azealic acid, used in a mixture or alone, and the 25 to 0 mole of the other aliphatic, cycloaliphatic or aromatic diacid is selected from fumaric acid, maleic anhydride, phthalic anhydride, isophthalic acid, 1,3-cyclohexanedicarboxylic acid, 1,2-cyclohexanedicarboxylic acid, used in a mixture or alone.

The cycloaliphatic or linear chain diol containing 2 to 16 carbon atoms of the second optional carboxyl functional semi-crystalline polyester (c) is selected from ethylene glycol, 1,3-propanediol, 1,4-butanediol, 1,5-pentanediol, 1,6-hexanediol, 1,7-heptanediol, 1,8-octanediol, 1,9-nonanediol, 1,10-decanediol, 1,12-dodecanediol, 1,14-tetradecanediol, 1,16-hexadecanediol or 1,4-cyclohexanediol, 1,4-cyclohexanedimethanol, hydrogenated Bisphenol A, 2,2,4,4-tetramethyl-1,3-cyclobutanediol or 4,8-bis(hydroxymethyl)tricyclo[5.2.1.0^{2,6}]decane, used as mixture or alone, and the 25 to 0 mole% of the other aliphatic glycol is selected from propylene glycol, neopentyl glycol, 2-methyl-1,3-propanediol, 2-butyl-2-ethyl-1,3-propanediol, hydroxypivalate of neopentyl glycol, used alone or in admixture.

Both carboxyl functional semi-crystalline polyesters (b) and (c) of the present invention can be linear or branched.

- 5 When branching is needed, incorporation of up to 15 mole %, based on the total of diacids, of polyacids having at least three carboxyl acid groups, such as pyromellitic acid or trimellitic acid or their corresponding anhydrides or of up to 15 mole% based on the amount of diols, of trifunctional or tetrafunctional polyols such as trimethylolpropane, di-trimethylolpropane, pentaerythritol or mixtures of them can be performed.

10

Both carboxyl functional semi-crystalline polyesters (b) and (c) of the present invention have an acid number (AN) from 10 to 50 mg KOH/g and preferably from 20 to 40 mg KOH/g.

They are further characterized by:

- 15 - a number averaged molecular weight (Mn) ranging from 2200 to 17000 and preferably from 2800 to 8500;
- a fusion zone from 30 to 150°C, measured by Differential Scanning Calorimetry (DSC) according to ASTM D3418 with a heating gradient of 20°C per minute;
- 20 - a glass transition temperature (Tg) from -50 to +50°C, measured by Differential Scanning Calorimetry (DSC) according to ASTM D3418 with a heating gradient of 20°C per minute;
- a degree of crystallinity, measured by Differential Scanning Calorimetry (DSC) according to ASTM D3415 of at least 5 J/g and preferably at least 10 J/g;
- an ICI (cone/plate) viscosity according to ASTM D4287-88, measured at 175°C ranging from 5 to 20000 mPa.s.

25

Both carboxyl group containing semi-crystalline polyesters (b) and (c) may fulfill one or more of the above conditions for the acid number, the number averaged molecular weight, the fusion zone, the glass transition temperature, the degree of crystallinity and the ICI viscosity. Preferably, the semi-crystalline polyesters, however, fulfill all of the above requirements.

30

The glycidyl group containing acrylic copolymer (d) of the present composition is preferably composed of 10 to 90 mole% of a glycidyl group containing monomer and from 90 to 10 mole% of other monomers copolymerisable with the glycidyl group containing monomer.

- 35 The glycidyl group containing monomer used in the acrylic copolymer of the present composition may be selected from, for example, glycidyl acrylate, glycidyl methacrylate, methyl glycidyl methacrylate, methyl glycidyl acrylate, 3,4-epoxycyclohexylmethyl

(meth)acrylate and acrylic glycidyl ether. These monomers can be used singly or in combination of two or more.

The other monomers of the acrylic copolymer copolymerisable with the glycidyl group
5 containing monomer may be selected from:

- 40 to 100 mole percentage of acrylic or methacrylic ester monomers such as methyl
acrylate, ethyl acrylate, n-propyl acrylate, isopropyl acrylate, n-butyl acrylate, n-decyl
acrylate, methyl methacrylate, ethyl methacrylate, n-propyl methacrylate, isopropyl
10 methacrylate, n-butyl methacrylate, isobutyl methacrylate, n-amyl methacrylate, n-hexyl
methacrylate, isoamyl methacrylate, allyl methacrylate, sec-butyl methacrylate, tert-
butyl methacrylate, 2-ethylbutyl methacrylate, cinnamyl methacrylate, crotyl
methacrylate, cyclohexyl methacrylate, cyclopentyl methacrylate, methallyl
methacrylate, n-octyl methacrylate, 2-ethylhexyl methacrylate, 2-phenylethyl
15 methacrylate and phenyl methacrylate.
- 0 to 60 mole percentage of other ethylenically unsaturated copolymerisable monomers
such as styrene, alkyl-substituted styrenes and chloro-substituted styrenes, acrylonitrile,
vinyl chloride, vinylidene fluoride and vinyl acetate.

20

The glycidyl group containing acrylic copolymers of the present composition preferably have an epoxy equivalent weight of 1.0 to 7.0 and preferably from 1.5 to 5.0 milliequivalents of epoxy/gram of polymer.

25 The glycidyl group containing acrylic copolymers may further be characterised by:


- a number averaged molecular weight (M_n) ranging from 1.000 to 10000, measured by gel permeation chromatography (GPC);
- 30 - a glass transition temperature (T_g) from 40 to 85°C, measured by Differential Scanning Calorimetry (DSC), according to ASTM D3418 with a heating gradient of 20°C per minute;
- an ICI (cone/plate) viscosity determined by the ICI method at 200°C ranging from 50 to
35 50000 mPa.s.

The glycidyl group containing acrylic copolymer may fulfill one or more of the above conditions for its epoxy equivalent weight, its number averaged molecular weight, its glass

transition temperature and its ICI viscosity. Preferably, the acrylic copolymer, however, fulfills all of the above requirements.

The curing agent (e) in accordance to the present invention, having functional groups reactive with the polyesters' carboxyl groups is a β -hydroxyalkylamide.

The β -hydroxyalkylamides, preferably used in the present invention, answer the general structure as represented in Formula I.




Wherein:

- A represents a mono- or polyvalent organic group derived from a saturated or unsaturated alkyl group with 1 to 60 carbon atoms, or an aryl group, or a trialkene amino group with 1 to 4 carbon atoms per alkylene group, or a carboxy-alkenyl group, or an alkoxy carbonyl-alkenyl
- R₁ represents hydrogen, an alkyl group with 1 to 5 carbon atoms or a hydroxy alkyl group with 1 to 5 carbon atoms

R₂ and R₃ are the same or different and each independently represents hydrogen or a straight or branched alkyl group with 1 to 5 carbon atoms, while one of the groups R₂ and one of the groups R₃ may also form, together with the adjacent carbon atoms, a cycloalkyl group.

Preferably, the β -hydroxyalkylamide is according the following Formula II:



- Where n is between 0.2 and about 1, and R₃ is an hydrogen (Primid XL552 from EMS) or a methyl group (Primid QM1260 from EMS).

The carboxyl group containing amorphous polyester and the carboxyl group containing semi-crystalline polyesters of the present composition are preparable using conventional esterification techniques well known in the art. The polyesters are prepared according to a procedure consisting of one or more reactive steps.

For the preparation of these polyesters, a conventional reactor equipped with a stirrer, an inert gas (nitrogen) inlet, a thermocouple, a distillation column connected to a water-cooled condenser, a water separator and a vacuum connection tube can be used.

- 5 The esterification conditions used to prepare the polyesters are conventional, namely a standard esterification catalyst, such as dibutyltin oxide, dibutyltin dilaurate, n-butyltin trioctoate, sulphuric acid or a sulphonic acid, can be used in an amount from 0.05 to 1.50% by weight of the reactants and optionally, colour stabilisers, for example, phenolic antioxidants such as Irganox 1010 (Ciba) or phosphonite- and phosphite-type stabilisers such as tributylphosphite, can be added in an amount from 0 to 1% by weight of the reactants.

- 15 Polyesterification is generally carried out at a temperature which is gradually increased from 130°C to about 190 to 250°C, first under normal pressure, then, when necessary, under reduced pressure at the end of each process step, while maintaining these operating conditions until a polyester is obtained, which has the desired hydroxyl and/or acid number. The degree of esterification is followed by determining the amount of water formed in the course of the reaction and the properties of the obtained polyester, for example the hydroxyl number, the acid number, the molecular weight or the viscosity.

- 20 When polyesterification is complete, cross-linking catalysts can optionally be added to the polyester while it is still in the molten state. These catalysts are added in order to accelerate cross-linking of the thermosetting powder composition during curing. Examples of such catalysts include amines (e.g. 2-phenylimidazoline), phosphines (e.g. triphenylphosphine), ammonium salts (e.g. tetrabutylammonium bromide or tetrapropylammonium chloride),
25 phosphonium salts (e.g. ethyltriphenylphosphonium bromide or tetrapropylphosphonium chloride). These catalysts are preferably used in an amount of 0 to 5% with respect of the weight of the polyester.

- The glycidyl group containing acrylic copolymer is preparable by conventional polymerisation techniques, either in mass, in emulsion, or in solution in an organic solvent. The nature of the solvent is very little of importance, provided that it is inert and that it readily dissolves the monomers and the synthesised copolymer. Suitable solvents include toluene, ethyl acetate, butyl acetate, xylene, etc. The monomers are copolymerised in the presence of a free radical polymerisation initiator (benzoyl peroxide, dibutyl peroxide, azo-bis-isobutyronitrile, and the like) in an amount representing 0.1 to 4.0% by weight of the monomers.

To achieve a good control of the molecular weight and its distribution, a chain transfer agent, preferably of the mercaptan type, such as n-dodecylmercaptan, t-dodecanethiol, iso-

octylmercaptan, or of the carbon halide type, such as carbon tetrabromide, bromotrichloromethane, etc., is also added in the course of the reaction. The chain transfer agent is used in amounts of up to 10% by weight of the monomers used in the copolymerisation.

- 5 A cylindrical, double walled reactor equipped with a stirrer, a condenser, an inert gas (nitrogen, for example), inlet and outlet, and metering pump feed systems are generally used to prepare the glycidyl group containing acrylic copolymer.

- 10 Polymerisation can be carried out under conventional conditions. Thus, when polymerisation is carried out in solution, for example, an organic solvent is introduced into the reactor and heated to reflux temperature under an inert gas atmosphere (nitrogen, carbon dioxide, and the like) and a homogeneous mixture of the required monomers, free radical polymerisation initiator and chain transfer agent, when needed, is then added to the solvent gradually over several hours. The reaction mixture is then maintained at the indicated temperature for some hours, while
15 stirring. The copolymer obtained is subsequently freed from the solvent in vacuo.

Preferably, the binder system of the thermosetting powdered composition of the present invention comprises, based on the total weight of the binder:

- 20 - 20 to 89.5, preferably 30 to 70 parts by weight of the carboxyl group containing amorphous isophthalic acid containing polyester (a),
- 5 to 50, preferably 5 to 30 parts by weight of the carboxyl group containing aliphatic semi-crystalline polyester, (b),
- 25 - 0 to 50, preferably 5 to 30 parts by weight of the carboxyl group containing semi-crystalline polyester (c);
- 5 to 40, preferably 5 to 25 parts by weight of the glycidyl group containing acrylic
30 copolymer (d), and
- 0.5 to 10.0, preferably 1 to 5 parts by weight of the β -hydroxyalkylamide curing agent (e).
- 35 The binder system of the thermosetting composition of the present invention is preferably composed in such a way that for each equivalent of carboxyl group present in the amorphous polyester (a) and semi-crystalline polyesters (b) and (c) there is between 0.3 and 2.0 and preferably between 0.6 and 1.7 equivalents of epoxy groups from the acrylic copolymer (d) and

between 0.2 and 1.2 and preferably between 0.4 and 1.0 equivalents of reactive functional groups of the β -hydroxyalkylamide curing agent (e).

5 The thermosetting polyester blend (a, b and c), when needed, can be obtained by dry blending the amorphous and the semi-crystalline polyesters using a mechanical mixing procedure as available for the premixing of the powder paint constituents.

10 Alternatively the amorphous and the semi-crystalline polyesters can be blended in the melt using a conventional cylindrical double-walled reactor or by extrusion such as with the Betol BTS40.

15 In addition to the essential components described above, compositions within the scope of the present invention can also include one or more additive(s) such as catalysts, fillers, flow control agents such as Resiflow PV5 (Worlee), Modaflow (Monsanto), Acronal 4F (BASF), etc., and degassing agents such as benzoin (BASF) etc. To the formulation UV-light absorbers such as Tinuvin 900 (Ciba), hindered amine light stabilisers represented by Tinuvin 144 (Ciba), other stabilising agents such as Tinuvin 312 and 1130 (Ciba), antioxidants such as Irganox 1010 (Ciba) and stabilisers from the phosphonite or phosphite type can be added.

20 Both, pigmented systems as well as clear lacquers can be prepared.

25 A variety of dyes and pigments can be utilised in the composition of this invention. Examples of useful pigments and dyes are metallic oxides such as titaniumdioxide, ironoxide, zincoxide and the like, metal hydroxides, metal powders, sulphides, sulphates, carbonates, silicates such as ammoniumsiliate, carbon black, talc, china clay, barytes, iron blues, lead blues, organic reds, organic maroons and the like.

30 The components of the composition according to the invention may be mixed by dry blending in a mixer or blender (e.g. drum mixer). The premix is then homogenised at temperatures ranging from 70 to 150°C in a single screw extruder such as the BUSS-Ko-Kneter or a double screw extruder such as the PRISM or APV. The extrudate, when cooled down, is grounded to a powder with a particle size preferably ranging from 10 to 150 μ m.

35 The powdered composition may be deposited on the substrate by use of a powder gun such as an electrostatic CORONA gun or TRIBO gun. On the other hand well known methods of powder deposition such as the fluidised bed technique can be used. After deposition the powder is heated to a temperature between 160 and 320°C, causing the particles to flow and fuse together to form a smooth, uniform, continuous, uncratered coating on the substrate surface.

Thus, the present invention further relates to the use of the above described compositions as powdered varnish or paint or for the preparation of a powdered varnish or paint. The invention further relates to the powdered varnishes or paints consisting of or comprising the present powdered thermosetting composition.

Furthermore, the present invention relates to a method of preparing a coating on a substrate comprising the steps of applying the above varnish or paint to the substrate and heating the coated substrate to fuse and cure the powdered varnish or paint to obtain the coating.

Furthermore, the present invention also refers to a coating preparable by the above method and a substrate entirely or partially coated with such coating.

The following examples are submitted for a better understanding of the invention but are not intended to restrict the invention thereto.

If not otherwise stated, all amounts are given in parts by weight.

Besides the abbreviations already defined above, OHN stands for hydroxyl number and T_m stands for fusion zone.

Example 1:

One step synthesis of a carboxyl functional amorphous polyester

423.4 parts of neopentyl glycol are placed in a conventional four neck round bottom flask equipped with a stirrer, a distillation column connected to a water cooled condenser, an inlet for nitrogen and a thermocouple attached to a thermoregulator.

The flask contents are heated, while stirring under nitrogen, to a temperature of circa 130°C at which point 719.6 parts of isophthalic acid and 2.5 parts of n-butyltintriocatoate are added. The heating is continued gradually to a temperature of 230°C. Water is distilled from the reactor from 180°C on. When distillation under atmospheric pressure stops, a vacuum of 50 mm Hg is gradually applied. After three hours at 230°C and 50 mm Hg, following characteristics are obtained:

	AN	34 mg KOH/g
	OHN	3 mg KOH/g
35	ICI200°C (cone/plate)	2100 mPa.s
	T _g (DSC, 20°/min)	60°C

Example 2:

Two step synthesis of a carboxyl functional amorphous polyester

424.87 parts of neopentyl glycol are placed in a conventional four neck round bottom flask as in example 1.

The flask contents are heated, while stirring under nitrogen, to a temperature of circa 130°C at which point 324.0 parts of terephthalic acid and 285.9 parts of isophthalic acid and 2.2 parts of n-butyltintriocatoate are added. The heating is continued gradually to a temperature of 230°C. Water is distilled from the reactor from 180°C on. When distillation under atmospheric pressure stops, a vacuum of 50 mm Hg is gradually applied. After three hours at 230°C and 50 mm Hg, following characteristics are obtained:

	AN	9 mg KOH/g
10	OHN	57 mg KOH/g

To the first step prepolymer standing at 200°C, 111.3 parts of isophthalic acid are added. Thereupon, the mixture is gradually heated to 230°C. After a 2 hour period at 230°C and when the reaction mixture is transparent, a vacuum of 50 mm Hg is gradually applied. After 3 hours at 230°C and 50 mm Hg, following characteristics are obtained:

15	AN	31 mg KOH/g
	OHN	3 mg KOH/g
	ICI200°C (cone/plate)	4400 mPa.s
	Tg (DSC, 20°/min)	54°C

20 Example 3 to 5:

Accordingly the procedure as described in example 1, the amorphous polyesters of example 3 and example 4 are prepared.

Example 5 is prepared accordingly the procedure as for example 2. In a first step a terephthalic acid-neopentyl glycol prepolymer with hydroxyl number of 50 mg KOH/g is prepared. The hydroxyl functionalised prepolymer put into reaction with isophthalic acid giving a carboxyl functionalised amorphous polyester with acid number of 30 mg KOH/g.

Table 1

	Example 3	Example 4	Example 5
neopentyl glycol	385.4	350.1	391.1
1,6-hexanediol		61.8	
trimethylolpropane	24.1	14.3	
isophthalic acid	733.6	716.1	85.2
terephthalic acid			664.7
AN, mg KOH/g	52	31	33
OH, mg KOH/g	4	3	4
ICI200°C, mPa.s	4700	2700	4500
Tg (DSC 20°C/min), °C	54	58	67

Example 6 to 9:

5 Synthesis of carboxyl functional semi-crystalline polyesters

The 2 polyesters of examples 6 and 7 whose composition and properties are given in Table 2, are carboxyl functional aliphatic semi-crystalline polyesters (b), according to the invention. The 2 polyesters of examples 8 and 9 are carboxyl functional semi-crystalline polyesters (c), whose presence is optional in the thermosetting powder compositions according to the invention.

10

Table 2

	Example 6	Example 7	Example 8	Example 9
1,4-cyclohexanedimethanol	398.4	438.3	530.3	
1,6-hexanediol				454.9
trimethylolpropane		15.9	15.9	
adipic acid			589.3	
sebacic acid		668.7		
1,12-dodecanedioic acid	697.7			
terephthalic acid				591.8
isophthalic acid				92.0
AN, mg KOH/g	33	35	21	30
OH, mg KOH/g	2	2	1	1
ICI200°C, mPa.s	600	100	6400	3000
Tm (DSC 20°C/min), °C	52	44	100	130

The carboxyl functional semi-crystalline polyesters of example 6 to 8 are prepared accordingly the procedure as for example 1.

The carboxyl functional semi-crystalline polyesters of example 9 is prepared accordingly the procedure as for example 2 where the isophthalic acid is put into reaction with an terephthalic acid-1,6-hexanediol based prepolymer with hydroxyl number of 40 mg KOH/g.

Example 10:

Preparation of the glycidyl group containing acrylic copolymer

800 parts of n-butyl acetate are brought in a double walled flask of 5 l equipped with a stirrer, a water cooled condenser, an inlet for nitrogen and a thermocouple attached to a thermoregulator. The flask content is then heated and stirred continuously while nitrogen is purged through the solvent. At a temperature of 125°C a mixture of 38.5 parts of tert-butylperoxybenzoate in 200 parts of n-butyl acetate are fed in the flask during 215 minutes with a peristaltic pump. 5 minutes after this start another pump is started with the feeding of a mixture of 132 parts of styrene, 585 parts of glycidyl methacrylate, 123 parts of butyl methacrylate and 160 parts of methyl methacrylate, during 180 minutes. The synthesis takes 315 minutes.

After evaporation of the n-butyl acetate an acrylic copolymer with following characteristics is obtained:

ICI viscosity @200°C	3500 mPa.s
Mn	5800

Example 11 to 13

Accordingly the procedure as described in example 10, the acrylic copolymers of example 11 to example 13, answering the compositions as in table 3, were prepared.

Table 3

	example 11	example 12	example 13
glycidyl methacrylate	563	565	284
butyl methacrylate	200		312
methyl methacrylate	200	345	312
t-butyl peroxybenzoate	25	91	91
Mn	8400	1900	2600
ICI200°C, mPa.s	30000	24000	40000

Example 14

The polyesters and acrylic copolymers as illustrated above, are then formulated to a powder accordingly to one of the formulations as mentioned below.

Formulation A		Formulation B	
White paint formulation		Brown paint formulation	
Binder	74.00	Binder	78.33
Kronos 2310	24.67	Bayferrox 130	4.44
Resiflow PV5	0.99	Bayferrox 3950	13.80
Benzoin	0.34	Carbon Black FW2	1.09
		Resiflow PV5	0.99
		Benzoin	0.35

5

The composition of the binders is given in Table 4, where the binders 1 to 3 are according to the invention and binders 4 to 6 are comparative.

Table 4

10

	Binder 1	Binder 2	Binder 3	Binder 4*	Binder 5*	Binder 6*
Amorphous polyester	595	527	553	570	592	645
Semi-crystalline polyester(s)	255	225	238	245	254	276
Acrylic copolymer	130	228	180	185	129	
Primid XL552	20	20	29			
TGIC					25	79

* The binders 4 to 6 are comparative

For the preparation of the powder formulation, the carboxyl functionalised isophthalic acid rich amorphous polyester resin and the carboxyl functionalised semi-crystalline polyester resins can be used as a blend or as separate resins. When used as a blend, blending is done by mixing the respectively resins in the molten state using a conventional round bottom flask.

The powders are prepared first by dry blending of the different components and then by homogenisation in the melt using a PRISM 16 mm L/D 15/1 twin screw extruder at an extrusion temperature of 85°C. The homogenised mix is then cooled and grinded in an Alpine UPZ100. Subsequently the powder is sieved to obtain a particle size between 10 and 110 µm. The powder thus obtained is deposited on cold rolled steel, by electrostatic deposition using the GEMA -

Volstatic PCG 1 spray gun. At a film thickness between 50 and 80 μm the panels are transferred to an air-ventilated oven, where curing proceeds for 18 minutes at a temperature of 200°C.

The paint characteristics for the finished coatings obtained from formulation A (example 15 to 33) and from formulation B (examples 34 to 37) with binder compositions as specified in table 4, are reproduced in table 5. In this table example 29 to example 33 are given by way of comparative examples.

Table 5

	Binder	Amorphous Polyester (a)	Aliphatic semi-crystalline polyester (b)	Semi-crystalline polyester (c)	Acrylic copolymer (d)	Gloss 60°	DI	RI
Formulation A								
Ex 15	1	Ex 1	Ex 6 - 33	Ex 8 - 66	Ex 10	71	200	200
Ex 16	1	Ex 1	Ex 6 - 50	Ex 8 - 50	Ex 10	46	160	160
Ex 17	1	Ex 1	Ex 6 - 66	Ex 8 - 33	Ex 10	28	140	120
Ex 18	1	Ex 1	Ex 6 - 100		Ex 10	20	100	80
Ex 19	3	Ex 3	Ex 6 - 66	Ex 8 - 33	Ex 11	30	120	100
Ex 20	1	Ex 1	Ex 7 - 66	Ex 8 - 33	Ex 10	65	140	160
Ex 21	3	Ex 3	Ex 7 - 66	Ex 9 - 33	Ex 11	45	200	200
Ex 22	3	Ex 3	Ex 7 - 33	Ex 9 - 66	Ex 11	58	100	120
Ex 23	1	Ex 2	Ex 6 - 66	Ex 8 - 33	Ex 10	29	120	120
Ex 24	1	Ex 2	Ex 6 - 100		Ex 10	22	100	100
Ex 25	1	Ex 4	Ex 6 - 50	Ex 8 - 50	Ex 12	45	180	160
Ex 26	1	Ex 4	Ex 6 - 33	Ex 8 - 66	Ex 12	65	200	180
Ex 27	2	Ex 4	Ex 6 - 33	Ex 8 - 66	Ex 13	55	120	100
Ex 28	1	Ex 5	Ex 6 - 66	Ex 8 - 33	Ex 10	44	100	20
Ex 29*	3	Ex 3		Ex 8 - 33 Ex 9 - 66	Ex 11	88	120	80
Ex 30*	1	Ex 1		Ex 8 - 100	Ex 10	89	200	200
Ex 31*	4	Ex 1	Ex 6 - 66	Ex 8 - 33	Ex 10	29	40	20
Ex 32*	5	Ex 1	Ex 6 - 66	Ex 8 - 33	Ex 10	25	40	20
Ex 33*	6	Ex 1	Ex 6 - 66	Ex 8 - 33		68	0	0
Formulation B								
Ex 34	1	Ex 1	Ex 6 - 33	Ex 8 - 66	Ex 10	74	180	200
Ex 35	1	Ex 1	Ex 6 - 66	Ex 8 - 33	Ex 10	30	140	140
Ex 36	1	Ex 2	Ex 6 - 66	Ex 8 - 33	Ex 10	29	120	100
Ex 37	1	Ex 5	Ex 6 - 66	Ex 8 - 33	Ex 10	40	80	20

* Examples 29 to 33 are comparative.

In this table:

Column 1 : indicates the identification number of the formulation

Column 2 : indicates the binder composition

5 Column 3 : indicates the type of amorphous polyester (a)

Column 4 : indicates the type and weight% of aliphatic semi-crystalline polyester (b) on the sum polyesters (b) + (c)

Column 5 : indicates the type and weight% of semi-crystalline polyester optionally used according to the invention, on the sum of polyesters (b) + (c)

10 Column 6 : indicates the type of acrylic copolymer (d)

Column 7 : indicates the 60° gloss, measured according to ASTM D523

Column 8 : indicates the direct impact strength according to ASTM D2794. The highest impact which does not crack the coating is recorded in kg.cm

Column 9 : indicates the reverse impact strength according to ASTM D2794. The highest
15 impact which does not crack the coating is recorded in kg.cm

For all the coatings as obtained from the different formulations (accordingly the invention as well as from those of the comparative examples), a very smooth visual perception, free of any defects, is perceived.

Besides, the different coatings of the formulations according to the invention (examples 15 to
20 28), all have a flexibility of 0T or 1T maximum, according to the ASTM D4145-83 T-bending test. For the comparative examples (examples 29 to 33), T-bending values equal to or higher than 2T are observed.

As clearly appears from table 5, the aliphatic semi-crystalline polyester containing linear aliphatic C10 - C16 dicarboxylic acids is necessary for having coatings proving reduced gloss
25 (example 16 versus example 30 and example 19 versus example 29). Changing the type of linear aliphatic dicarboxylic acid results in a modified gloss level (example 17 versus example 20).

It also appears that increasing the amount of the aliphatic semi-crystalline polyester containing linear aliphatic C10 - C16 dicarboxylic acids, in the binder composition, induces a proportional
30 gloss reduction of the coating derived (example 15 to example 18, example 21 versus example 22, example 23 versus example 24, example 25 versus example 26).

Also, it appears that increasing the amount of terephthalic acid in the amorphous carboxyl functional polyester, within the preferred range of the present invention, does not influence the coating properties as long as gloss and flexibility are concerned.

35 Increasing the terephthalic acid content to a proportion where it becomes preponderant to the isophthalic acid content, influences gloss and flexibility (example 17 versus example 23 versus example 28).

Increasing the acrylic equivalent weight influences gloss and flexibility of the derived paint film (example 26 versus example 27).

The presence of the β -hydroxyalkylamide hardener is necessary for getting a paint film proving flexibility (example 17 versus example 31).

- 5 Replacing the β -hydroxyalkylamide hardener by a glycidyl group containing hardener, well known in the art, such as triglycidylisocyanurate (TGIC), has no influence on the gloss level, yet tremendously reduces paint flexibility (example 17 versus example 32).

- Replacing the hardener system of the present invention (glycidyl containing acrylic copolymer and β -hydroxyalkylamide) by a hardener generally used in commercial powder coatings
10 intended for outdoor applications, such as triglycidylisocyanurate, results in coatings proving a complete lack of flexibility (example 17 versus example 33).

From all these examples it clearly appears that for getting a flexible low gloss or semi-matt powder coating from a formulation obtained in a single extrusion process, the powder formulation necessarily must comprise:

- 15 • a carboxyl functional isophthalic acid containing amorphous polyester, from which the acid constituent is composed of at least 10 mole% of isophthalic acid and preferably of 50 mole% of isophthalic acid;
- an aliphatic carboxyl functional semi-crystalline polyester, derived from linear chain C10 - C16 aliphatic dicarboxylic acids, preferably in combination with another carboxyl
20 functional semi-crystalline polyester;
- a glycidyl group containing acrylic copolymer for reacting with the polyester carboxylic acid groups;
- a β -hydroxyalkylamide group containing cross-linking agent.

- Besides, the coatings according to the present invention all prove to satisfy an excellent outdoor
25 resistance, comparable to or better than the currently used nowadays commercial available powders.

- In table 6, the relative 60° gloss values, recorded every 400 hours, according to ASTM D523, are reported for the coating obtained from examples 34 and 35, submitted to the Q-UV accelerated weathering test. In the same table (comparison) are given the weathering results of a
30 carboxylic acid functionalised amorphous polyester obtained by reacting 400,6 parts of neopentyl glycol, 22,3 parts of trimethylolpropane and 724,7 parts of isophthalic acid, in the same manner as in example 3.

- This polyester has an AN of 32 mg KOH/g and a Tg of 59°C, determined by DSC with a heating rate of 20°C/min. This polyester is formulated in a 93/7 ratio with PT810 according to
35 the brown paint formulation as in formulation B.

In this table only gloss reductions until 50% of the maximum value are mentioned. Weathering measurements are conducted in a very severe environment, i.e. the Q-UV accelerated weathering tester (Q-Panel Co) according to ASTM G53-88 (standard practice for operating light and

water exposure apparatus - fluorescent UV/condensation type - for exposure of non metallic materials).

For this table, coated panels have been subjected to the intermittent effects of condensation (4 hours at 50°C) as well as the damaging effects of sunlight simulated by fluorescent UV-A lamps (340 nm, I = 0.77 W/m²/nm) (8 hours at 60°C).

Table 6

Hours	UV-A (340 nm, I = 0.77 W/m ² /nm)		
	Formulation B example 34	Formulation B example 35	Comparison
0	100	100	100
400	100	99	100
800	99	100	100
1200	98	97	97
1600	98	96	97
2000	97	97	97
2400	98	96	96
2800	99	94	95
3200	98	88	92
3600	95	85	89
4000	90	86	87
4400	87	84	84
4800	84	80	79
5200	78	75	76
5600	77	71	73
6000	74	67	67
6400	53	59	59
6800	54	50	54
7200	47	41	49
7600	40		

Claims:

1. Powdered thermosetting composition including a binder which comprises
 - 5 (a) a carboxyl group containing amorphous isophthalic acid containing polyester,
 - (b) a carboxyl group containing aliphatic semi-crystalline polyester,
 - (c) optionally, a carboxyl group containing semi-crystalline polyester other than (b)
 - (d) at least 5 parts by weight, based on the total weight of the binder, of a glycidyl group containing acrylic copolymer, said copolymer comprising at least 10 mole% of a
10 glycidyl group containing monomer and having a number averaged molecular weight (Mn) of 10000 or less, and
 - (e) a β -hydroxyalkylamide group containing curing agent whose functional groups are reactive with the polyesters' carboxyl groups.
- 15 2. Composition according to claim 1, wherein the carboxyl group containing amorphous isophthalic acid containing polyester (a) consists of 10-100 mole% isophthalic acid and 0-90 mole% of another diacid, based on the total of the acid constituents, and 35-100 mole% neopentyl glycol and/or 2-butyl-2-ethyl-1,3-propanediol and 0-65 mole% of another diol, based on the total of the alcohol constituents.
- 20 3. Composition according to claim 1 or 2, wherein the carboxyl group containing amorphous isophthalic acid containing polyester further contains up to 15 mole% of polyacids relative to the diacids and/or up to 15 mole% of polyols, relative to the neopentylglycol and/or 2-butyl-2-ethyl-1,3-propanediol.
- 25 4. Composition according to any of claims 1 to 3, wherein the carboxyl group containing amorphous isophthalic acid containing polyester (a) has an acid number (AN) from 15-70 mg KOH/g, a number averaged molecular weight (Mn) from 1600 to 11000, a glass transition temperature (Tg) from 40-80°C and an ICI (cone/plate) viscosity at 200°C from 5-15000 mPa.s.
- 30 5. Composition according to any of claims 1-4, wherein the carboxyl group containing semi-crystalline aliphatic polyester (b) consists of 40-100 mole% of linear chain dicarboxylic acid containing 10 to 16 carbon atoms and 0-60 mole% of at least one linear chain dicarboxylic acid containing 4 to 9 carbon atoms, based on the total of the acid constituents, and at least one
35 aliphatic non-branched or cycloaliphatic diol containing 2 to 16 carbon atoms, as the alcohol constituent.

6. Composition according to any of claims 1-5, wherein the optional carboxyl group containing semi-crystalline polyester (c) consists of 75-100 mole% of 1,4-cyclohexanedicarboxylic acid and/or terephthalic acid and/or a linear chain dicarboxylic acid containing 4 to 9 carbon atoms, and of 0-25 mole% of another aliphatic, cycloaliphatic or aromatic diacid, based on the total of the acid constituents, and 75-100 mole% of a cycloaliphatic or linear chain diol containing 2 to 16 carbon atoms and 0-25 mole% of another aliphatic diol, based on the total of the alcohol constituents.
7. Composition according to claims 5 or 6, wherein the carboxyl group containing semi-crystalline polyesters (b) and (c) further contains up to 15 mole% of polyacids relative to the 1,4-cyclohexanedicarboxylic acid and/or terephthalic acid and/or linear chain dicarboxylic acid, and/or up to 15 mole% of polyols, relative to the diols.
8. Composition according to any of the preceding claims, wherein the carboxyl group containing semi-crystalline polyesters (b) and (c) both have an acid number (AN) from 10-50 mg KOH/g, a number averaged molecular weight (Mn) from 2200-17000, a fusion zone from 30-150°C, a glass transition temperature (Tg) from -50 to 50°C, a degree of crystallinity of at least 5 J/g and an ICI (cone/plate) viscosity at 175°C from 5-20000 mPa.s.
9. Composition according to any of the preceding claims, wherein the glycidyl group containing acrylic copolymer consists of 10-90 mole% of a glycidyl group containing monomer selected from the group consisting of glycidyl acrylate, glycidyl methacrylate, methyl glycidyl acrylate, methyl glycidyl methacrylate, 3,4-epoxycyclohexylmethyl acrylate, 3,4-epoxycyclohexylmethyl methacrylate, acrylic glycidyl ether and mixtures thereof and 10-90 mole% of monomers copolymerisable with the glycidyl group containing monomers.
10. Composition according to any of the preceding claims, wherein the glycidyl group containing acrylic copolymer has an epoxy equivalent weight of 1.0 to 7.0 milliequivalent of epoxy/gram of polymer, a number averaged molecular weight (Mn) ranging from 1000 to 10000, a glass transition temperature (Tg) from 40-85°C and an ICI (cone/plate) viscosity at 200°C from 60-50000 mPa.s.
11. Composition according to any of the preceding claims, wherein the binder comprises, based on the total weight of the binder,
- (a) 20 to 89.5 parts by weight of the carboxyl group containing amorphous isophthalic acid containing polyester,

- (b) 5 to 50 parts by weight of the carboxyl group containing aliphatic semi-crystalline polyester,
- (c) 0 to 50 parts by weight of the carboxyl group containing semi-crystalline polyester other than (b);
- 5 (d) 5 to 40 parts by weight of the glycidyl group containing acrylic copolymer, and
- (e) 0.5 to 10.0 parts by weight of the β -hydroxyalkylamide group containing curing agent.

12. Composition according to any of the preceding claims, further comprising one or more additive(s) selected from the group consisting of catalysts, fillers, flow control agents, degassing
10 agents, UV-light absorbers, light stabilizers, antioxidants and other stabilizers.

13. Composition according to any of the preceding claims, further comprising one or more dyes and/or pigments, such as metal oxides, metal hydroxides, metal powders, sulphides, sulphates, carbonates, silicates, carbon black, talc, china clay, barytes, iron blue, lead blue,
15 organic reds and organic maroons.

14. Method of preparing a composition as claimed in any of claims 1-13 comprising the steps of blending the components of the composition to prepare a premix, homogenising the premix at an elevated temperature such as 70-150°C and grounding the homogenised product to
20 obtain the powdered thermosetting composition.

15. Method according to claim 14, wherein in a first step the amorphous polyester and the semi-crystalline polyesters are dry blended or melt blended.

25 16. Use of a composition as claimed in any of claims 1-13 as powdered varnish or paint or for the preparation of a powdered varnish or paint.

17. Powdered varnish or paint consisting of or comprising a composition as claimed in any of claims 1-13.

30

18. Method of preparing a coating on a substrate comprising the steps of applying a powdered varnish or paint as claimed in claim 17 to the substrate and heating the coated substrate to fuse and cure the powdered varnish or paint to obtain the coating.

35 19. Coating, preparable by the method of claim 18.

20. Substrate entirely or partially coated with the coating of claim 19.

INTERNATIONAL SEARCH REPORT

onal Application No
PCT/EP 01/14889

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C09D167/02

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C09D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 91 14745 A (COURTAULDS COATINGS HOLDINGS) 3 October 1991 (1991-10-03) cited in the application	
A	EP 0 038 635 A (DAINIPPON INK & CHEMICALS) 28 October 1981 (1981-10-28) abstract	1,9
A	EP 0 551 064 A (UCB SA) 14 July 1993 (1993-07-14) cited in the application	
A	WO 00 55267 A (VALSPAR CORP) 21 September 2000 (2000-09-21) claim 1	1,4,8

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

A document defining the general state of the art which is not considered to be of particular relevance

E earlier document but published on or after the international filing date

L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

O document referring to an oral disclosure, use, exhibition or other means

P document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

8 document member of the same patent family

Date of the actual completion of the international search

6 May 2002

Date of mailing of the international search report

16/05/2002

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Decocker, L

INTERNATIONAL SEARCH REPORT

International Application No
PCT/EP 01/14889

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 9114745	A	03-10-1991	AT 138967 T	15-06-1996
			AU 656890 B2	23-02-1995
			AU 7559791 A	21-10-1991
			BR 9106278 A	13-04-1993
			CS 9100811 A2	17-12-1991
			DE 69120061 D1	11-07-1996
			DE 69120061 T2	02-01-1997
			DK 521992 T3	14-10-1996
			EP 0521992 A1	13-01-1993
			ES 2088493 T3	16-08-1996
			WO 9114745 A1	03-10-1991
			GB 2244060 A ,B	20-11-1991
			GR 3020671 T3	31-10-1996
			HU 62640 A2	28-05-1993
			HU 213530 B	28-07-1997
			KR 185652 B1	01-05-1999
			PL 166308 B1	31-05-1995
			US 6184311 B1	06-02-2001
EP 0038635	A	28-10-1981	JP 1649850 C	30-03-1992
			JP 3002915 B	17-01-1991
			JP 56136856 A	26-10-1981
			DE 3169322 D1	25-04-1985
			EP 0038635 A1	28-10-1981
EP 0551064	A	14-07-1993	US 4499239 A	12-02-1985
			AT 164871 T	15-04-1998
			DE 69225058 D1	14-05-1998
			DE 69225058 T2	15-10-1998
			EP 0551064 A2	14-07-1993
			ES 2117659 T3	16-08-1998
			JP 6271811 A	27-09-1994
			KR 232422 B1	01-12-1999
			US 5436311 A	25-07-1995
WO 0055267	A	21-09-2000	US 5525370 A	11-06-1996
			AU 3628200 A	04-10-2000
			EP 1165711 A1	02-01-2002
			WO 0055267 A1	21-09-2000

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record.**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☒ FADED TEXT OR DRAWING
- ☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.

THIS PAGE BLANK (USPTO)